

ESD Tests for Carolina Performance Fabrics S.A. de C.V.

Fabric: CAROSTAT 150

agosto 11, 2008

Static Decay Per Fed. Std 101C, Method 4046 - Seconds

@12% RH, 73 degrees F, 48 hours

	+ 5 kV	- 5kV
1	0.01	0.01
2	0.01	0.01
3	0.01	0.01

Instrument Used: ETS 406D Static Decay Meter



Fowler

3551 Moore-Duncan Hwy.
Moore, SC 29369

Tel: 864-574-6415 Email: sfowler@sfowler.com

Stephen L. Fowler

Stephen L. Fowler

The data and conclusions of this report are based upon the information and samples supplied to Fowler Associates for the tests described herein. Product users should make his or her own tests to determine the suitability of the information and conclusions herein stated or implied for their intended use, and shall assume all risk and liability in connection therein.