

Resistance Between Various Points
Carolina Performance Fabrics S.A de C.V.

Style: Caroclean LM

The following tests were conducted in general agreement with the ESD Association's Test Method STM 2.1-1997 @100 volts

This garment meets the requirements of the Groundable Static Control Garment System (ANSI/ESD STM 2.1) and ANSI/ESD 20.20

Tests @ 12% RH, 72°F

5 lb. Probes

Wash Cycles	Point to Point 1	Point to Point 2	Point to Point 3	Point to Point 4	Point to Point 5	Point to Point 6
As Received	2.39 X 10 ⁶	2.37 X 10 ⁶	2.12 X 10 ⁶	2.10 X 10 ⁶	2.17 X 10 ⁶	1.94 X 10 ⁶
After 3 Washes	2.48 X 10 ⁶	2.70 X 10 ⁶	2.52 X 10 ⁶	2.23 X 10 ⁶	2.44 X 10 ⁶	2.11 X 10 ⁶
After 100 Washes	2.48 X 10 ⁶	2.20 X 10 ⁶	2.56 X 10 ⁶	2.52 X 10 ⁶	2.85 X 10 ⁶	2.43 X 10 ⁶

Stephen S Fowler



Fowler

Associates, Inc. January 30, 2012

The data and conclusions of this report are based upon the information and samples supplied to Fowler Associates for the tests described herein. Product users should make his or her own tests to determine the suitability of the information and conclusions herein stated or implied for their intended use, and shall assume all risk and liability in connection therein.

3551 Moore-Duncan Highway Moore, SC 29369-9719 Phone: 864-574-6415 FAX: 864-576-4992

Email: sfowler@sfowler.com Web Site: www.sfowler.com